




Rihan Trade



R25

| Applications for R15 |
|------------------------------------|
| • Water based decorative paints. |
| • Solvent based decorative paints. |
| • Protective coatings. |
| • Rubber moldings. |
| • Adhesive and sealants. |

| Raw Material Physical Properties | |
|----------------------------------|----------------------|
| True specific gravity | 2.7g/cm ³ |
| Hardness: (Mohs) | 3 |

| Chemical Compound | Percentage |
|--------------------------------|------------|
| CaCO ₃ | 99.5% |
| MgO | 0.1% |
| Al ₂ O ₃ | 0.01% |
| Fe ₂ O ₃ | 0.01% |
| SiO ₂ | 0.1% |
| CaO | 56.5% |
| LOI | 43.5% |

| Physical Properties | |
|-------------------------------|------------------------|
| Brightness (RY)±1% | 96% |
| pH value | 9 Max |
| Linseed oil absorption (±0.5) | 19.5g/100gm |
| Bulk density (±0.5) | 0.57 g/cm ³ |
| HCl insoluble content | 0.3 Max |
| Moisture content | 0.2% Max |

| Technical Data | |
|-----------------------|-----------|
| Top Cut D97 | 25.0 ±1 μ |
| D50 | 5 ±1 μ |
| Finner than 2 microns | 23 ±2 % |

